

Telf. 902 929 084 Web: <http://www.niberma.com> E-mail: info@niberma.com

PRODUCTO	NIBERMAFLEX 251/T 4,4MM
-----------------	--------------------------------

1. Technical specifications

Purpose: Technical data determining the quality of floorcovering in rolls conforming to GPHSZ-038

2. Main characteristics

Designations: sports-flooring, with moderate flame spread on flameproof concrete subfloor

Film: PVC

3. Technical Data of the Product

Parameter	Specification	Tolerance	Test method
Thickness mm	4,4	+ - 0,2	MSZ EN 428
Linear change in dimensions % - length	+ - 0,2	max.	MSZ EN 434
Residual indentation mm	0,35	max.	MSZ EN 433
Peel resistance N/50mm - length	50	min.	MSZ EN 431
Peel resistance N/50mm - cross	50	min.	MSZ EN 431
Colour-fastness to light	6	min.	MSZ EN 20105 B02. 3m
Chemical resistance - 50% ethyl alcohol contact time 120 min	no change	appr.	MSZ EN 423
Chemical resistance - 5% fatty alcohol sulphonate contact time 120 min	no change	appr.	MSZ EN 423
Chemical resistance - 5% acetic acid contact time 120 min	no change	appr.	MSZ EN 423
Chemical resistance - petrol contact time 120 min	no change	appr.	MSZ EN 423
Wear layer thickness mm	0,7	min.	MSZ EN 429
Width cm	200	min.	MSZ EN 426

Telf. 902 929 084 Web: <http://www.niberma.com> E-mail: info@niberma.com

4. Informative data

Parameter	Specification	Tolerance	Test method
Weight g/m ²	2890	kb	MSZ EN 430

Niberma podrá modificar las características de esta ficha técnica sin previo aviso.
 Esta ficha es de carácter informativo y sustituye a las anteriores. Niberma no se hará responsable de su uso indebido.

Julio 2013